

广州新莱福磁材有限公司
Guang Zhou Newlife Magnetics Co.,Ltd.

产品仕様书

SUPPLY SPECIFICATION SHEET

客户名称: 保加利亚 RL
Customer:

品名: 磁胶
Part Name: Magnetic sheeting

型号: NF04
Drawing No.:

日期:
Date: 2023-8-21

批准 Comfirmer	审核 Auditor	编制 Editor
汪晓阳	吴隆章	任治家
承认签署: APPROVED BY:		

规格 (Size) :

- 1、NF04 料 15M×1000×0.4mm/MUV/2.0mm Pole pitch/Matte white pvc
- 2、NF04 料 15M×1000×0.5mm/MUV/2.0mm Pole pitch/Matte white pvc
- 3、NF04 料 15M×1000×0.65mm/MUV/2.0mm Pole pitch/Matte white pvc
- 4、NF04 料 15M×1000×0.8mm/MUV/2.0mm Pole pitch/Matte white pvc
- 5、NF04 料 15M×1270×0.5mm/MUV/2.0mm Pole pitch/Matte white pvc
- 6、NF04 料 15M×1270×0.65mm/MUV/2.0mm Pole pitch/Matte white pvc
- 7、NF04 料 15M×1270×0.8mm/MUV/2.0mm Pole pitch/Matte white pvc
- 8、NF04 料 20M×1270×0.4mm/MUV/2.0mm Pole pitch/Matte white pvc
- 9、NF04 料 30M×620×0.4mm/MUV/2.0mm Pole pitch/Matte white pvc
- 10、NF04 料 30M×620×0.5mm/MUV/2.0mm Pole pitch/Matte white pvc
- 11、NF04 料 30M×620×0.65mm/MUV/2.0mm Pole pitch/Matte white pvc
- 12、NF04 料 30M×620×0.8mm/MUV/2.0mm Pole pitch/Matte white pvc

尺寸和公差 (Dimensions: & Tolerance) :

Item	Length (m)	Width (mm)	Thickness (mm)				Thickness of PVC (mm)
			0.4	0.5	0.65	0.8	
Size	15	1000	0.4	0.5	0.65	0.8	0.1
Tolerance	0/+0.6	-1/+5	±0.04	±0.05	±0.05	±0.08	±0.01

Item	Length (m)		Width (mm)	Thickness (mm)				Thickness of PVC (mm)
	15	20		0.4	0.5	0.65	0.8	
Size	15	20	1270	0.4	0.5	0.65	0.8	0.1
Tolerance	0/+0.6		-1/+5	±0.04	±0.05	±0.05	±0.08	±0.01

Item	Length (m)	Width (mm)	Thickness (mm)				Thickness of PVC (mm)
			0.4	0.5	0.65	0.8	
Size	30	620	0.4	0.5	0.65	0.8	0.1
Tolerance	0/+0.6	-1/+3	±0.04	±0.05	±0.05	±0.08	±0.01

磁性能 (Magnetic Properties) :

Code	Br(Gs)	Hcb(Oe)	Hcj(Oe)	(BH)max (MGOe)
NF04	≥ 1400	≥ 1000	≥ 1600	0.50-0.65

吸力 (Pull Strength) :

Code	Thickness (mm)	Pole pitch (mm)	Pull (g/cm ²)
NF04	0.4	2.0	≥ 17
NF04	0.5	2.0	≥ 24
NF04	0.65	2.0	≥ 32
NF04	0.8	2.0	≥ 41

物理参数 Physical Data:

Total thickness (mm) 总厚度	0.5±0.05	0.6±0.06	0.75±0.06	0.9±0.09
Reference Weight (g/m ²) 克重	1500±150	1840±190	2350±240	2860±290
Hardness (Shore D) 硬度	45±5	45±5	45±5	43±5
Flexibility (Φ6mm 铁 圆柱) 柔韧度	Without cracking	Without cracking	Without cracking	Without cracking
Opacity 不透明度	100%	100%	100%	100%

产品保存 Storage:

工作条件：参考在周边温度-20℃至+70℃范围内工作，实际应用环境客户需测试
For reference, it works within the range of - 20 °C to+70 °C of the ambient temperature, and the customer needs to test the actual application environment

储存条件：25℃和50%相对湿度

Storage Condition: 25° C and 50% humidity conditions

保质期:原包装状态下自生产之日起贮存期为12个月

磁胶经充磁后是永磁体，在常温使用条件下，无强磁干扰，磁性能不会消退。

Shelf life: 12 months under original packaging condition

The magnetic force is permanent and will not degrade in normal temperature without strong magnetic interference.

产品包装 Packing:



入箱示意图 in carton



打托示意图 in pallet (quantity per pallet will be as actual)